

**Version with markings to show amendments made:**

5. (Amended) [The adhesive coated article according to claim 1] An adhesive coated article comprising a substrate with a first and second major surface and a layer of microsphere adhesive on at least a portion of the first major surface of the substrate, wherein the microsphere adhesive comprises (a) a plurality of polymeric, solid, elastomeric microspheres that are the reaction product of reactants comprising polymerizable starting materials comprising at least one C<sub>4</sub>-C<sub>14</sub> alkyl (meth)acrylate ester monomers and at least one (meth)acrylamide comonomer with the proviso that <sup>→ no ant base</sup> the polar comonomer has no dissociable proton having a K<sub>d</sub> of greater than 10<sup>-3</sup>, (b) a polymeric stabilizer in an amount of about 0.1 to about 3 parts by weight per 100 parts by weight of the microspheres, and (c) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres.

6. (Amended) [The adhesive coated article according to claim 1] An adhesive coated article comprising a substrate with a first and second major surface and a layer of microsphere adhesive on at least a portion of the first major surface of the substrate, wherein the microsphere adhesive comprises (a) a plurality of polymeric, solid, elastomeric microspheres that are the reaction product of reactants comprising polymerizable starting materials comprising at least one C<sub>4</sub>-C<sub>14</sub> alkyl (meth)acrylate ester monomers and at least one polar comonomer with the proviso that if the polar comonomer has a dissociable proton, the polar comonomer has no dissociable proton having a K<sub>d</sub> of greater than 10<sup>-3</sup>, (b) a polymeric stabilizer in an amount of about 0.1 to about 3 parts by weight per 100 parts by weight of the microspheres, and (c) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres.

7. (Amended) [The adhesive coated article according to claim 1] An adhesive coated article comprising a substrate with a first and second major surface and a layer of microsphere adhesive on at least a portion of the first major surface of the substrate, wherein the microsphere adhesive comprises (a) a plurality of polymeric, elastomeric microspheres wherein the microspheres are the reaction

product of polymerizable, starting materials comprising at least one C<sub>4</sub>-C<sub>14</sub> alkyl (meth)acrylate ester monomer and at least one (meth)acrylamide comonomer, (b) an initiator for the polymerizable monomer starting materials present in amounts ranging from 0.1 to approximately 2 parts by weight per 100 part by weight of the polymerizable monomer starting materials, (c) optionally, a polymeric stabilizer in an amount of between about 0.1 and about 3 parts by weight per 100 parts by weight of the microspheres, (d) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres, and (e) a chain transfer agent in an amount sufficient to produce 30-98% of a solvent-soluble portion in the microspheres.

9. (Amended) The adhesive coated article according to claim [4] 5 wherein the microsphere adhesive comprises (a) a plurality of polymeric, elastomeric microspheres wherein the microspheres are the reaction product of polymerizable, starting materials comprising at least one C<sub>4</sub>-C<sub>14</sub> alkyl (meth)acrylate ester monomer, (b) an initiator for the polymerizable monomer starting materials present in amounts ranging from 0.1 to approximately 2 parts by weight per 100 part by weight of the polymerizable monomer starting materials, (c) optionally, a polymeric stabilizer in an amount of between about 0.1 and about 3 parts by weight per 100 parts by weight of the microspheres, (d) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres, and (e) a chain transfer agent in an amount sufficient to produce 30-98% of a solvent-soluble portion in the microspheres.

11. (Amended) [The adhesive coated article according to claim 1] An adhesive coated article comprising a substrate with a first and second major surface and a layer of microsphere adhesive on at least a portion of the first major surface of the substrate, wherein the microsphere adhesive comprises a plurality of hollow, polymeric, acrylate, inherently tacky, infusible, solvent-insoluble, solvent dispersible, pressure sensitive microspheres comprising (a) at least about 85 parts by weight of at least one alkyl acrylate ester or alkyl methacrylate ester, and (b) up to about 15 parts by weight of at least one (meth)acrylamide monomer, wherein a majority of the

[illegible]